

3M™ Scotch-Weld™ Structural Adhesive Film AF 191

is a family of thermosetting modified epoxy structural adhesives in film form that are available in a variety of weights and carriers.

3M™ Scotch-Weld™ Structural Adhesive Film AF 191 is a proven adhesive film with excellent mechanical properties. Scotch-Weld AF 191 Films delivers years of industry success and proven performance for over 30 years, backed by 3M's technical service and support.

- High fracture toughness and peel strength
- 350°F (177°C) Cure Excellent long-term elevated temp properties
- Available unsupported for reticulation
- Available with copper mesh for lightning strike surfacing



3M[™] Scotch-Weld[™] Structural Adhesive Film AF 191

Structure	Product	Color	Film Weight (± .005 lb/ft²)	Film Weight (± 24.4 g/m²)	Film Thickness (mils)	Recom. Cure Temp	Recom. Cure Time	Volatile Content	Size	Stock Number
Unsupported	AF 191U	Clear	0.055	244	8	350°F (177°C)	1 Hour	Less than 1.5%	36in x 3yds	62-3072-5306-2
									36in x 50yds	62-3072-5309-6
	AF 191U	Clear	0.035	170	6				36in x 3yds	62-3053-5306-2
									36in x 50yds	62-3053-5309-6
	AF 191U	Clear	0.015	73	2.5				48in x 3yds	62-3068-6006-5
	711 1010	Oloui	0.010	70	2.0				48in x 36yds	62-3068-6005-7
Matte Scrim	AF 191M	Pale Yellow	0.060	293	10	350°F (177°C)	1 Hour	Less than 1.5%	36in x 3yds	62-2608-5305-6
									36in x 50yds	62-2608-5301-5
	AF 191M	Amber	0.035	170	6				36in x 3yds	62-3151-5306-4
									36in x 50yds	62-3151-5309-8
	AF 191M	Amber	0.030	146	5				36in x 3yds	62-2707-5306-4
	AI IJIW	Amboi	0.000	140	0				36in x 50yds	62-2707-5309-8
Knit Scrim	AF 191K	Clear	0.100	488	16	350°F (177°C)	1 Hour	Less than 1.5%	36in x 3yds	62-3142-5306-3
									36in x 50yds	62-3142-5309-7
	AF 191K	Amber	0.080	390	13				36in x 3yds (Lt Green Liner)	62-3384-5305-3
	AI IVIN								36in x 50yds (Yellow Liner)	62-3384-5309-5

Get what you need, when you need it...

Contact your 3M Aerospace Sales Representative for more information on:

Other sizes available
Low MOQs
30-day lead times on many adhesive films

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

