

3M Advanced Materials Division

3M™ Nextel™ Ceramic Sleeveings 312 and 440

Introduction

3M™ Nextel™ Ceramic Sleeveings 312 are made from continuous Nextel 312 Alumina-Boria-Silica fibers, and retain strength and flexibility at continuous temperatures of up to 2192°F (1200°C).

3M™ Nextel™ Ceramic Sleeveings 440 are made from continuous Nextel 440 Alumina-Boria-Silica fibers, and retain strength and flexibility at continuous temperatures of up to 2372°F (1300°C).

Features and Benefits

- Non-oxidizing
- Non-hygroscopic
- Good chemical resistance
- Low thermal conductivity
- Good abrasion resistance
- Fire and flame resistant

Important Processing Information

Heat Cleaning: Nextel ceramic sleeveings 312 and 440 are coated during manufacture with sizings or finishes to serve as aids in textile processing. The sizings or finishes consist of organic polymers which, when first heated, may ignite and/or decompose to potentially hazardous byproducts or process contaminants. See Safety Data Sheet or contact 3M for more information.

Heat Treating: If Nextel ceramic sleeveings 312 are to be subjected to hot humid environments for extended

Typical Applications

Application	3M™ Nextel™ Ceramic Sleeveings	
	312	440
Continuous Use Temperature*	2192°F (1200°C)	2372°F (1300°C)
Aerospace Cable and insulation wrap, fire zone cable protection, flame barrier, thermal shields		
Industrial Cable and insulation ties, hose protection, heater wire insulation, fire zone cable protection, door seals		
Electrical Heater wire insulation, thermocouple insulation		

*40% fiber strength retention tested at room temperature after 100 hours soak.

periods of time (e.g., 95°C @ 100% relative humidity for ten days), heat treating is necessary. Heat treatment changes the crystal structure of the fiber preventing physical degradation in these conditions.

Heat cleaning or heat treating of Nextel ceramic sleeveings are services offered by 3M.

Additional Information

For additional information about 3M Nextel ceramic sleeveings, please call **1-800-367-8905**, or contact your local 3M representative.



Typical Properties (Not for specification purposes.)

3M™ Nextel™ Ceramic Sleeveings 312 and 440

Sleeving Inside Diameter		Wall Thickness (sized)		Length per Unit Weight on Mandrel (sized)		Target Yield As Packaged, Roll Form (sized)		Picks per Unit Length	
inch	mm	inch	mm	yards/lb	m/kg	yards/lb	m/kg	picks/inch	picks/cm
3M™ Nextel™ Ceramic Sleeveing 312, Style AS-40									
1/16	1.6	0.028	0.71	85	171	87	175	13	5
1/8	3.2	0.037	0.94	39	79	42	85	11	4
1/4	6.4	0.038	0.97	25	50	28	56	11	4
1/2	12.7	0.038	0.97	13	26	16	32	10	4
3/4	19.1	0.038	0.97	8.7	18	12	24	10	4
1	25.4	0.033	0.84	7.7	16	9.6	19	12	5
1 1/2**	38.1	0.033	0.84	5.4	11	7.2	15	12	5
2**	50.8	0.038	0.97	3.6	7.3	5.4	11	11	4
2 1/2**	63.5	0.037	0.94	3.1	6.2	4.4	8.9	8	3
3M™ Nextel™ Ceramic Sleeveing 440, Style BS-40									
1/16**	1.6	0.027	0.69	76	153	76	153	13	5
1/8	3.2	0.038	0.97	35	71	38	77	12	5
1/4	6.4	0.035	0.89	23	46	25	50	11	4
1/2	12.7	0.039	0.99	12	24	15	30	10	4
3/4**	19.1	0.038	0.97	7.9	16	10	20	10	4
1**	25.4	0.033	0.84	7.0	14	8.6	17	12	5

AS-40 Input yarn is 900 denier 3M Nextel Plied Yarn 312, 1/2, 2.7z.
 BS-40 Input yarn is 1000 denier 3M Nextel Plied Yarn 440, 1/2, 2.7z.
 **Available only by special order.

Warranty, Limited Remedy, and Disclaimer: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Export Control: The 3M product(s) listed here may be controlled commodities under applicable U.S. export control laws and regulations, including, but not limited to, the U.S. International Traffic in Arms Regulations (ITAR) and the Export Administration Regulations (EAR). These laws and regulations may, among other things, prohibit the export and/or reexport of controlled product(s) to any or all locations outside of the United States without prior U.S. Government export authorization, the sharing of export controlled technical data and services with those anywhere who are not U.S. citizens or U.S. permanent residents, dealings with U.S. Government, United Nations and other "Restricted Parties," and proliferation activities including those that further nuclear, chemical, or biological warfare, missile stockpiling/use, or the use of rockets or unmanned aerial vehicle systems. 3M and purchasers or prospective purchasers of the 3M product(s) shall comply with all applicable export control laws and regulations, which may require obtaining and maintaining applicable export control authorization or licenses, and understand that the ability of a party to obtain or maintain such authorization or license is not guaranteed. The exporter of record has the sole responsibility to determine whether the export or subsequent reexport of the 3M product(s) requires export authorization. An explicit condition to 3M selling or making available the 3M product(s) is the customer's agreement to comply with all applicable trade compliance laws and regulations.



3M Advanced Materials Division
 3M Center
 St. Paul, MN 55144 USA

Phone 1-800-367-8905
 Web www.3M.com/ceramics

3M and Nextel are trademarks of
 3M Company. Used under license by
 3M subsidiaries and affiliates.

Please recycle. Printed in USA. © 3M 2016.
 All rights reserved. Issued: 7/16 11700HB
 98-0400-2983-1 Rev. B