

3M™ Aerospace Sealant AC-360 Class B

Product Description

3M™ Aerospace Sealant AC-360 Class B are fast cure, intermediate density two-component, manganese dioxide cure, polysulfide fuel tank and fuselage sealants. 3M AC-360 Class B Sealants have outstanding resistance to aviation gasoline and jet fuel, as well as resistance to chemicals and petroleum products common to the aircraft industry. 3M AC-360 Class B Sealants maintain flexibility and bond strength on most metal substrates such as; aluminum, titanium, steel, stainless steel, and many coatings under extremes of temperature, weathering and stress. The mixed compound is a thixotropic paste easily applied by extrusion, injection gun or spatula, and exhibits superb tooling properties.

Applications

- Sealing integral fuel tanks
- Repairing integral fuel tanks
- Sealing fuselages

Typical Physical and Application Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Color Base: Accelerator:	Off White Brown
Mix Ratio	100 base / 10 accelerator (by weight)
Nonvolatile Content	98%
Base Viscosity (RVF Brookfield #7 spindle) @ 2 rpm, 77°F)	7,500 - 11,000 poise

Application Life and Cure Time

(@ 77°F, 50% Relative Humidity)

	Minimum Application Life¹	Typical Tack- Free Time²	Typical Cure Time³
B-1/2	1/2 hour	2-3 hours	2-3 hours
B-2	2 hours	8 hours	8 hours

¹Application life refers to the length of time that mixed compound remains at a consistency suitable for application with spatula or caulking gun. Application life is always measured at a standard temperature of 77°F with a relative humidity level of 50%. In general, for every 20°F rise in temperature, the application life is halved; and for every 20°F drop, it is doubled. High humidity levels during the mixing process will shorten application life.

²Tack-free time is the length of time after which a mixed sealant will no longer tightly adhere to L-LP-690 standard low density polyethylene film.

³Cure time is defined as the length of time it takes 3M™ Aerospace Sealant AC-360 Class B to reach 30A hardness. It depends on three factors: remaining application life, temperature and relative humidity. To a certain extent, the temperature/humidity factors for application life also apply to curing. To accelerate the curing process, apply heat up to (but not more than) 120°F.

Typical Physical and Performance Properties of Cured Compound after 14 Days @ 77°F/50% RH

Color (mixed)	Dark Brown
Specific Gravity	1.40 max
Hardness	50-55 Shore "A"
Low Temperature Flexibility	No cracking, checking or adhesion loss when tested at -65°F (-54°C)
Service Temperatures	-65° to +250°F (-54° to +121°C)
Short Term Service Temperature	-65° to +360°F (-54° to +182°C)
Weight Loss in JRF	5.22%
Thermal Rupture Resistance	Conforms
Corrosion	None
Repairability	45 piw / 100% cohesive failure

3M™ Aerospace Sealant AC-360 Class B

Typical Values of 3M™ Aerospace Sealant AC-360 Class B

Tensile Strength and % Elongation

Conditioning	Specification Requirements	Results
Standard Cure	200 psi / 200%	274 psi / 550%
+ 7 days JRF	125 psi / 150%	300 psi / 780%
+ 7 days in BMS-3-11 ty IV	60 psi / 200%	160 psi / 800%

Peel Strength

Substrate	Conditioning	Load / % Cohesion
MIL-P-23377 RT Cure	7 days @ 140°F in DI Water 7 days @ 140°F in NaCl	80 lbs. / 100% 75 lbs. / 100%
MIL-PRF-85582	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl	38 lbs. / 100% 48 lbs. / 100%
AS 4/3501-6 (epoxy graphite, peel)	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	40 lbs. / 100% 50 lbs. / 100% 47 lbs. / 100%
AS 4/3501-6 (epoxy graphite, tool)	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	43 lbs. / 100% 50 lbs. / 100% 47 lbs. / 100%
IM7/5250-4 (graphite/BMI, peel)	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	43 lbs. / 100% 50 lbs. / 100% 47 lbs. / 100%
IM7/5250-4 (graphite/BMI, tool)	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	44 lbs. / 100% 48 lbs. / 100% 47 lbs. / 100%
AMS 2471 Anodized	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	60 lbs. / 100% 65 lbs. / 100% 47 lbs. / 100%
MIL-C-27725	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 70 days @ 140°F in JRF 70 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	62 lbs. / 100% 70 lbs. / 100% 45 lbs. / 100% 46 lbs. / 100% 50 lbs. / 100%
AMS 4911 Titanium	7 days @ 140°F in JRF 7 days @ 140°F in JRF/NaCl 70 days @ 140°F in JRF 70 days @ 140°F in JRF/NaCl 6 temp cycles in JRF/NaCl	65 lbs. / 100% 70 lbs. / 100% 45 lbs. / 100% 48 lbs. / 100% 48 lbs. / 100%
MIL-C-5541	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	64 lbs. / 100% 74 lbs. / 100%

Peel Strength (continued)

Substrate	Conditioning	Load / % Cohesion
MIL-A-8625 Ty.1	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	60 lbs. / 100% 65 lbs. / 100%
MIL-S-5059 (302)	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	55 lbs. / 100% 58 lbs. / 100%
MIL-S-9046 Ty. I, Comp. B	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	66 lbs. / 100% 70 lbs. / 100%
BMS 10-20 Ty. II, Grade A	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	65 lbs. / 100% 70 lbs. / 100%
BMS 10-11 Ty. I, Grade A	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	70 lbs. / 100% 65 lbs. / 100%
BMS 10-11 Ty. I, Grade E	7 days @ 140°F in JRF 7 days @ 140°F in 3% NaCl	59 lbs. / 100% 72 lbs. / 100%
DMS-1786	No immersion	48 lbs. / 100%
DMS-1850	No immersion	45 lbs. / 100%

Health and Safety Precaution

3M™ Aerospace Sealant AC-360 Class B are safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request.

Storage

The shelf life of 3M™ Aerospace Sealant AC-360 Class B is 6 months from date of packaging, when stored at temperatures below 80°F in its original unopened container.

Mixed 3M AC-360 Class B Sealants may be stored under refrigeration as follows:

15 days at -10°F
28 days at -40°F

It is important to remember that freezing, storing and thawing procedures reduce application life. Also, frozen storage will reduce application life by varying amounts depending on the storage temperature and length of storage time. All aspects of storage, freezing and thawing should be planned carefully and it is not recommended to mix and freeze with less than 1/2 hour of available application time.

3M™ Aerospace Sealant AC-360 Class B

For Additional Information

In the U.S., call toll free 1-800-235-2376, or fax 1-800-435-3082 or 651-737-2171. For U.S. Military, call 1-866-556-5714. If you are outside of the U.S., please contact your nearest 3M office or one of the following branches:

Australia 61-2-498-9711 tel 61-2-498-9710 fax	Austria 01-86686-298 tel 01-86686-229 fax	Brazil 55 19 3838-7876 tel 55 19 3838-6892 fax	Canada 800-410-6880 ext. 6018 tel 800-263-3489 fax
China 86-21-62753535 tel 86-21-62190698 fax	Denmark 45-43-480100 tel 45-43-968596 fax	France 0810-331-300 tel 30-31-6195 fax	Germany 02131-14-2344 tel 02131-14-3647 fax
Italy 02-7035-2177 tel 02-7035-2125 fax	Japan 03-3709-8245 tel 03-3709-8743 fax	Korea 02-3771-4114 tel 02-786-7429 fax	Netherlands 31-71-5-450-272 tel 31-71-5-450-280 fax
South Africa 11-922-9111 tel 11-922-2116 fax	Spain 34-91-321-6000 tel 34-91-321-6002 fax	Switzerland 01-724-9114 tel 01-724-9068 fax	United Kingdom (0) 161-237-6174 tel (0) 161-237-3371 fax

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

These products were manufactured under a 3M Quality Management System registered to the AS9100 standard.



Aerospace and Aircraft Maintenance Department

3M Center, Building 223-1N-14
St. Paul, MN 55144-1000
1-800-235-2376
www.3M.com/aerospace

3M is a trademark of 3M Company.
Please recycle. Printed in U.S.A.
©3M 2012 (2/12) All rights reserved.
60-9700-0333-5

